

TECHNICAL DATA SHEET
BASIC GLOSS ACRYLIC VARNISH



1. Description

Gloss Acrylic Vanish for the final finish of surfaces previously painted with Pinty Plus Fluorescent Paint. Suitable for the protection and decoration of different supports.

2. Properties:

- Great adherence
- Good colour and gloss retention
- High transparence
- Excellent resistance to the atmospheric elements
- Great hardness and flexibility
- Very easy application
- Very fast drying

3. Recommended uses:

Suitable for use both indoors and outdoors. Recommended to project and decorate any kind of supports: metal, cardboard, stone, ceramics and many kinds of plastics. Ideal for D I Y, industry, automotion, plumbing ...

4. Presentation

Colours: Gloss F119

Cans: 270cc/200ml cans.

5. Technical Characteristics:

- | | |
|----------------------|--|
| • Nature | Thermoplastic acrylic resin |
| • Solvents | Ketones |
| • Propellant | Hydrocarbons, rich in C3 y C4 |
| • Density | 0.85 ± 0.01 gr./cc |
| • Viscosity | 12 – 13 seg. (Ford Cup Nr. 4, 20°C) |
| • % solids in weight | 15 % (Theoretical value) |
| • VOC | 648 gr./l (Depending on the colour) |
| • Gloss at 60° | > 90 |
| • Spreading: | 270/200ml: 1 m ² according to support |

- Drying time at 20°C: Superficial: 15 min.
Total: 30 min.
Repainted : After 15 minutes
- Application temperature from 10 up to 35°C
- Paint resistance to the heat Recommended up to 90°C
- Flammability Extremely flammable
- Pressure: 3-4 bars at 20°C
6-7 bars at 50°C
- Cleaning Cleaning solvent in spray
- Life of the product > 3 years

6. Instructions

The surface to be painted should be clean, dry and without any kind of pollutant.

Shake the can lightly. Spray at a distance for 25/30 minutes applying thin, quick and criss-cross layers. In order to achieve a uniform finish and avoid any vanishing, it is advisable to apply two thin layers instead of a thick one. At the end of the application, turn the can over and spray until only gas comes out.

7. Security

The aerosol can features the correspondent security indications which must be followed. For further information please check the Security Data Sheet.

The information provided in the present technical sheet is the result of the research undertaken in our laboratory as well as real experiences based on applications. Nevertheless due to the fact that quite often the products are used in conditions beyond our control, we cannot warranty the good results of the product if the application and use are not the correct ones.



NOVASOL SPRAY S.A.

Polígono Industrial Empalme
C/ Empalme, 27
Tel. 977 67 76 05 Fax. 977 67 80 72
43712 LLORENÇ DEL PENEDES (Tarragona)
novasol@novasolspray.com